



**MATERIAL TESTING LABORATORY**  
**MILITARY ENGINEER SERVICES (MES)**  
**TEST RESULTS FOR FINENESS MODULUS (F.M.) OF SAND**

Job No : 62/2015-16  
Name of Client : GE(Army) Savar.  
Ref Itr No : CEA/382 of 2014-2015  
Project Name : CEA/382 of 2014-15/17/E-4 dt. 21 Oct. 2015  
Sample Specimen : Local Sand  
Date of Sample Collection : Sunday, 25 October, 2015

Copy No : 01

Sieve Size	Wt of Material Retained (gms)	Percentage Material Retained (rounded)	Cumulative % Retained	% Finer	Remarks
#4	0	0	0		
#8	0	0	0		
#16	2	0.5	0.5		
#30	8	2	2.5		
#50	187	46.75	49.25		FM = 1.46
#100	177	44.25	93.5		
#200	18	4.5	....		
Pan	8	2	....		
			$\Sigma = 145.75$		

**Cautions:**

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the samples to be tested.
2. It is recommended that the samples are sent in a secured and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

**Observation on Specimen(if any):**

1. As the result is below the Std. value, So nec. measures to be taken as per contract
- 2.

Laboratory Technician

Test Performed By

Vetted By

This is a computer generated copy  
No signature is required

**Permissible Value:**

1. For Sylhet/Domar Sand minimum FM will be = 2.50
2. For Local Sand minimum FM will be = 1.50
3. For Vitty Sand minimum FM will be = 0.80