



MATERIAL TESTING LABORATORY

MILITARY ENGINEER SERVICES (MES)

TEST RESULTS FOR TENSILE STRENGTH OF PLAIN/DEFORMED/RIBBED COLD TWISTED M.S. BARS

Job No	: 90/15-16	Copy No.	: 5
Name of Client	: GE(Army) Maint.North,Dhaka	Sample Specimen	: Length 600 mm Dia 25mm
Ref Itr No	: CEA/424 of 2014-15/04/E-6 dt.20 Oct'2015	Sample Grade	: 60
Project Name	: CEA/424 of 2014-15	Frog Mark	: RSRM 400W
Date of Collection	: Wednesday, 11 November, 2015		

Sample No	Nominal Dia	Actual Dia	Area Under Test	Actual Unit Weight	Average Actual Unit Weight	Yield or Proof Load	Yield or Proof Strength	Average Yield or Proof Strength	Ultimate Load	Ultimate Strength	Average Ultimate Strength	Elongation % (gauge length)		Average Elongation % (gauge length)	
	inch mm	inch mm	sq.inch sq.mm	lb/ft kg/m	lb/ft kg/m	lb kn	psi Mpa	psi Mpa	lb kn	psi Mpa	psi Mpa	8inch	5d**	8inch	5d**
1	0.984 25	0.988 25.092	0.7609 490.8739	2.609 3.882	2.609 3.882	49763.94 221.36	65405 451	67278 464	80268.41 357.05	105498 727	107508 741	27		27	
2	0.984 25	0.988 25.092	0.7609 490.8739	2.609 3.882		54037.58 240.37	71022 490		84856.78 377.46	111528 769		26.5			
3	0.984 25	0.988 25.092	0.7609 490.8739	2.609 3.882		49763.94 221.36	65405 451		80268.41 357.05	105498 727		27			

Cautions:

1. Samples as supplied to the laboratory have been tested. The laboratory authority does not bear any responsibility as to the representative character of the samples to be tested.
2. It is recommended that the samples are sent in a secure and sealed cover/packet/container under signature of the competent authority.
3. In order to avoid fraudulent fabrication of the test results, it is recommended that all test reports should be collected by duly authorized person and not by the contractor/supplier.

Observation on Specimen(if any):

1.

Minimum Standard Requirements (BDS/ISO 6935-2:1991(E))				Minimum Standard Requirements (ASTM A615/A616M-96a)									
Grade	Y/strength	Ult.Str	Elongation	ASTM A 615 M			ASTM A 615 M			ASTM A 615/A 615 M			
	N/mm2 or Mpa	N/mm2 or Mpa	%	Grade	Y/strength psi (kg/cm2)	Ult.Str psi (kg/cm2)	Grade	Y/strength Mpa (kg/cm2)	Ult.Str Mpa (kg/cm2)	Minimum Elongation in 8"(203.2 mm) GL (%)			
									10 mm	13,16,19 mm	22,25 mm	29,32,36 mm	
300	300	330	16	40	40000(2810)	70000(4910)	300	300(3050)	500(5090)	11	12
400/400w	400	440	14	60	60000(4210)	90000(6310)	420	420(4275)	620(6295)	9	9	8	7
500/500w	500	550	14	75	75000(5255)	100000(7015)	520	520(5275)	690(7010)	..	7	7	6

This is a computer generated copy
No signature is required

Note : [1 Mpa = 145 Psi, 1 kg/cm2 = 14.223 psi]

Laboratory Technician

Test Performed By

Vetted By